



Standard Specification for Seamless Cold-Drawn Low-Carbon Steel Heat-Exchanger and Condenser Tubes¹

This standard is issued under the fixed designation A179/A179M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification² covers minimum-wall-thickness, seamless cold-drawn low-carbon steel tubes for tubular heat exchangers, condensers, and similar heat transfer apparatus.

1.2 This specification covers tubes $\frac{1}{8}$ to 3 in. [3.2 to 76.2 mm], inclusive, in outside diameter.

NOTE 1—Tubing smaller in outside diameter and having a thinner wall than indicated in this specification is available. Mechanical property requirements do not apply to tubing smaller than $\frac{1}{8}$ in. [3.2 mm] in outside diameter or with a wall thickness under 0.015 in. [0.4 mm].

1.3 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification. The inch-pound units shall apply unless the “M” designation of this specification is specified in the order.

2. Referenced Documents

2.1 *ASTM Standards*:³

A450/A450M Specification for General Requirements for Carbon and Low Alloy Steel Tubes

3. Ordering Information

3.1 Orders for material under this specification should include the following, as required, to describe the desired material adequately:

- 3.1.1 Quantity (feet, metres, or number of lengths),
- 3.1.2 Name of material (seamless tubes),
- 3.1.3 Manufacture (cold-drawn),

- 3.1.4 Size (outside diameter and minimum wall thickness),
- 3.1.5 Length (specific or random),
- 3.1.6 Optional requirements (product analysis, Section 9, flange test, 11.3),
- 3.1.7 Test report required (Certification Section of Specification A450/A450M),
- 3.1.8 Specification number, and
- 3.1.9 Special requirements.

4. General Requirements

4.1 Material furnished under this specification shall conform to the applicable requirements of the current edition of Specification A450/A450M, unless otherwise provided herein.

5. Manufacture

5.1 Tubes shall be made by the seamless process and shall be cold drawn.

6. Heat Treatment

6.1 Tubes shall be heat treated after the final cold draw pass at a temperature of 1200°F [650°C] or higher.

7. Surface Condition

7.1 Finished tubes shall be free of scale. A slight amount of oxidation will not be considered as scale.

8. Chemical Composition

8.1 The steel shall conform to the following requirements as to chemical composition:

Carbon, %	0.06–0.18
Manganese, %	0.27–0.63
Phosphorus, max, %	0.035
Sulfur, max, %	0.035

8.2 Supplying an alloy grade that specifically requires the addition of any element other than those listed in 8.1 is not permitted.

9. Product Analysis

9.1 When requested on the purchase order, a product analysis shall be made by the supplier from 1 tube per 250 pieces or when tubes are identified by heat, one tube per heat shall be analyzed. The chemical composition thus determined shall conform to the requirements specified.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.09 on Carbon Steel Tubular Products.

Current edition approved March 1, 2012. Published November 2012. Originally approved in 1935. Last previous edition approved in 2005 as A179/A179M – 90a (2005). DOI: 10.1520/A0179_A0179M-90AR12.

² For ASME Boiler and Pressure Vessel Code applications see related Specification SA-179 in Section II of that Code.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

9.2 If the original test for product analysis fails, retests of two additional billets or tubes shall be made. Both retests, for the elements in question, shall meet the requirements of the specification; otherwise all remaining material in the heat or lot (Note 2) shall be rejected or, at the option of the producer, each billet or tube may be individually tested for acceptance. Billets or tubes which do not meet the requirements of the specification shall be rejected.

NOTE 2—A lot consists of 250 tubes.

10. Hardness Requirements

10.1 The tubes shall have a hardness number not exceeding 72 HRB.

11. Mechanical Tests Required

11.1 *Flattening Test*—One flattening test shall be made on specimens from each of two tubes from each lot (Note 2) or fraction thereof.

11.2 *Flaring Test*—One flaring test shall be made on specimens from each of two tubes from each lot (Note 2) or fraction thereof.

11.3 *Flange Test*—When specified as a substitute for the flaring test, for tubes having a wall thickness (actual mean wall) less than 10 % of the outside diameter, one test shall be made on specimens from each of two tubes from each lot (Note

2) or fraction thereof. For tubes other than specified above, the flange test shall not be required.

11.4 *Hardness Test*—Rockwell hardness tests shall be made on specimens from two tubes from each lot. The term *lot* applies to all tubes, prior to cutting, of the same nominal diameter and wall thickness which are produced from the same heat of steel. When final heat treatment is in a batch-type furnace, a lot shall include only those tubes of the same size and the same heat which are heat treated in the same furnace charge. When the final heat treatment is in a continuous furnace, a lot shall include all tubes of the same size and heat, heat treated in the same furnace at the same temperature, time at heat, and furnace speed.

11.5 *Hydrostatic Test*—Each tube shall be subjected to the hydrostatic test, or, instead of this test, a nondestructive electric test may be used when specified by the purchaser.

12. Product Marking

12.1 In addition to the marking prescribed in Specification A450/A450M, the marking shall include the name and order number of the purchaser.

13. Keywords

13.1 cold drawn tube; condenser tubes; heat exchanger tubes; low carbon steel; seamless tube

EXPLANATORY NOTES

NOTE 1—For purposes of design, the following tensile properties may be assumed:

Tensile strength, min, ksi [MPa]	47 [325]
Yield strength, min, ksi [MPa]	26 [180]
Elongation in 2 in. or 50 mm, min, %	35

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).