

SPECIFICATION FOR CARBON STRUCTURAL STEEL



SA-36/SA-36M



(Identical with ASTM Specification A 36/A 36M-00a)

01
A02

1. Scope

1.1 This specification covers carbon steel shapes, plates, and bars of structural quality for use in riveted, bolted, or welded construction of bridges and buildings, and for general structural purposes.

1.2 Supplementary requirements are provided for use where additional testing or additional restrictions are required by the purchaser. Such requirements apply only when specified in the purchase order.

1.3 When the steel is to be welded, a welding procedure suitable for the grade of steel and intended use or service is to be utilized. See Appendix X3 of Specification A 6/A 6M for information on weldability.

1.4 For Groups 4 and 5 wide flange shapes for use in tension, it is recommended that the purchaser consider specifying supplementary requirements, such as fine austenitic grain size and Charpy V-notch impact testing.

1.5 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system is to be used independently of the other, without combining values in any way.

1.6 The text of this specification contains notes or footnotes, or both, that provide explanatory material. Such notes and footnotes, excluding those in tables and figures, do not contain any mandatory requirements.

1.7 For plates cut from coiled product, the additional requirements, including additional testing requirements and the reporting of additional test results, of A 6/A 6M apply.

2. Referenced Documents

2.1 ASTM Standards:

- A 6/A 6M Specification for General Requirements for Rolled Structural Steel Bars, Plates, Shapes, and Sheet Piling
- A 27/A 27M Specification for Steel Castings, Carbon, for General Application
- A 307 Specification for Carbon Steel Bolts and Studs, 60, 000 psi Tensile Strength
- A 325 Specification for High-Strength Bolts for Structural Steel Joints
- A 325M Specification for High-Strength Bolts for Structural Steel Joints [Metric]
- A 500 Specification for Cold-Formed Welded and Seamless Carbon Steel Structural Tubing in Rounds and Shapes
- A 501 Specification for Hot-Formed Welded and Seamless Carbon Steel Structural Tubing
- A 502 Specification for Steel Structural Rivets
- A 563 Specification for Carbon and Alloy Steel Nuts
- A 563M Specification for Carbon and Alloy Steel Nuts [Metric]
- A 570/A 570M Specification for Steel, Sheet and Strip, Carbon, Hot-Rolled, Structural Quality
- A 668/A 688M Specification for Steel Forgings, Carbon and Alloy, for General Industrial Use
- F 568M Specification for Carbon and Alloy Steel Externally Threaded Metric Fasteners

3. Appurtenant Materials

3.1 When components of a steel structure are identified with this ASTM designation but the product form is not listed in the scope of this specification, the material shall conform to one of the standards listed in Table 1 unless otherwise specified by the purchaser.

4. General Requirements for Delivery

4.1 Material furnished under this specification shall conform to the requirements of the current edition of Specification A 6/A 6M, for the ordered material, unless a conflict exists in which case this specification shall prevail.

4.1.1 Coiled product is excluded from qualification to this specification until decoiled, levelled, and cut to length. Plates produced from coil means plates that have been cut to individual lengths from a coiled product and are furnished without heat treatment. The processor decoils, levels, cuts to length, and marks the product. The processor is responsible for performing and certifying all tests, examinations, repairs, inspections, or operations not intended to affect the properties of the material. For plates produced from coils, two test results shall be reported for each qualifying coil. See Note 1.

NOTE 1 — Additional requirements regarding plate from coil are described in Specification A 6/A 6M.

5. Bearing Plates

5.1 Unless otherwise specified, plates used as bearing plates for bridges shall be subjected to mechanical tests and shall conform to the tensile requirements of Section 8.

5.2 Unless otherwise specified, mechanical tests shall not be required for plates over $1\frac{1}{2}$ in. [40 mm] in thickness used as bearing plates in structures other than bridges, subject to the requirement that they shall contain 0.20 to 0.33% carbon by heat analysis, that the chemical composition shall conform to the requirements of Table 2 in phosphorus and sulfur content,

and that a sufficient discard shall be made to secure sound plates.

6. Materials and Manufacture

6.1 The steel for plates and bars over $\frac{1}{2}$ in. [12.5 mm] in thickness and shapes other than Group 1 shall be semikilled or killed.

7. Chemical Composition

7.1 The heat analysis shall conform to the requirements prescribed in Table 2, except as specified in 5.2.

7.2 The steel shall conform on product analysis to the requirements prescribed in Table 2, subject to the product analysis tolerances in Specification A 6/A 6M.

8. Tension Test

8.1 The material as represented by the test specimen, except as specified in 5.2 and 8.2, shall conform to the requirements as to the tensile properties prescribed in Table 3.

8.2 Shapes less than 1 in.² [645 mm²] in cross-section and bars, other than flats, less than $\frac{1}{2}$ in. [12.5 mm] in thickness or diameter need not be subjected to tension tests by the manufacturer, provided that the chemical composition used is appropriate for obtaining the tensile properties in Table 3.

9. Keywords

9.1 bars; bolted construction; bridges; buildings; carbon; plates; riveted construction; shapes; steel; structural steel; welded construction

TABLE 1
APPURTENANT MATERIAL SPECIFICATIONS

NOTE 1 — The specifier should be satisfied of the suitability of these materials for the intended application. Chemical composition and/or mechanical properties may be different than specified in A 36/A 36M.

Material	ASTM Designation
Steel rivets	A 502, Grade 1
Bolts	A 307, Grade A or F 568M, Class 4.6
High-strength bolts	A 325 or A 325M
Steel nuts	A 563 or A 563M
Cast steel	A 27/A 27M, Grade 65–35 [450–240]
Forgings (carbon steel)	A 668, Class D
Hot-rolled sheets and strip	A 570/A 570M, Grade 36
Cold-formed tubing	A 500, Grade B
Hot-formed tubing	A 501
Anchor bolts	F 1554

TABLE 2
CHEMICAL REQUIREMENTS

NOTE 1 — Where "... " appears in this table, there is no requirement. The heat analysis for manganese shall be determined and reported as described in the heat analysis section of Specification A 6/A 6M.

Product Thickness, in. [mm]	Shapes ^A	Plates ^B						Bars		
		All	To 3/4 [20], Incl.	Over 3/4 to 1 1/2 [20 to 40], Incl.	Over 1 1/2 to 2 1/2 [40 to 65], Incl.	Over 2 1/2 to 4 [65 to 100], Incl.	Over 4 [100]	To 3/4 [20], Incl.	Over 3/4 to 1 1/2 [20 to 40], Incl.	Over 1 1/2 to 4 [40 to 100], Incl.
Carbon, max., %	0.26	0.25	0.25	0.25	0.26	0.27	0.29	0.26	0.27	0.28
Manganese, %	...	...	...	0.80-1.20	0.80-1.20	0.85-1.20	0.85-1.20	...	0.60-0.90	0.60-0.90
Phosphorus, max., %	0.04	0.04	0.04	0.04	0.04	0.04	0.04	0.04	0.04	0.04
Sulfur, max., %	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05
Silicon, %	0.40 max.	0.40 max.	0.40 max.	0.40 max.	0.15-0.40	0.15-0.40	0.15-0.40	0.40 max.	0.40 max.	0.40 max.
Copper, min., % when copper steel is specified	0.20	0.20	0.20	0.20	0.20	0.20	0.20	0.20	0.20	0.20

^A Manganese content of 0.85-1.35% and silicon content of 0.15-0.40% is required for shapes over 426 lb/ft [634 kg/m].

^B For each reduction of 0.01% point below the specified carbon maximum, an increase of 0.06% point manganese above the specified maximum will be permitted, up to the maximum of 1.35%.

TABLE 3
TENSILE REQUIREMENTS^A

Plates, Shapes,^B and Bars:	
Tensile strength, ksi [MPa]	58–80 [400–550]
Yield point, min., ksi [MPa]	36 [250] ^C
Plates and Bars^{D,E}:	
Elongation in 8 in. [200 mm], min., %	20
Elongation in 2 in. [50 mm], min., %	23
Shapes:	
Elongation in 8 in. [200 mm], min., %	20
Elongation in 2 in. [50 mm], min., %	21 ^B

^A See the Orientation subsection in the Tension Tests section of Specification A 6/A 6M.

^B For wide flange shapes over 426 lb/ft [634 kg/m], the 80 ksi [550 MPa] maximum tensile strength does not apply and a minimum elongation in 2 in. [50 mm] of 19% applies.

^C Yield point 32 ksi [220 MPa] for plates over 8 in. [200 mm] in thickness.

^D Elongation not required to be determined for floor plate.

^E For plates wider than 24 in. [600 mm], the elongation requirement is reduced 2% points. See Elongation Requirement Adjustments subsection under the Tension Tests section of Specification A 6/A 6M.

SUPPLEMENTARY REQUIREMENTS

These requirements shall not apply unless specified in the order. Standardized supplementary requirements for use at the option of the purchaser are listed in Specification A 6/A 6M. Those that are considered suitable for use with this specification are listed by title.

S5. Charpy V-Notch Impact Test

In addition, the following optional supplementary requirements are also suitable for use with this specification.

S97. Limitation on Rimmed Or Capped Steel

S97.1 The steel shall be other than rimmed or capped.

ADDITIONAL SUPPLEMENTARY REQUIREMENTS

In addition, the following optional supplementary requirements are also suitable for use with this specification.

S91. Fine Austenitic Grain Size

S91.1 The steel shall be killed and have a fine austenitic grain size.

S97. Limitation on Rimmed or Capped Steel

S97.1 The steel shall be other than rimmed or capped.